MAGNESIUM HYDROXIDE NikoMag® M7SV

APPLICATION:

A highly efficient non-toxic inorganic flame retardant. Perfect choice for production of PE, EVA, XLPE based compounds.

THE BASIC QUALITY PARAMETERS:

Parameter	Grade
	NikoMag® M7SV
1 Appearance	White powder
2 Mass fraction of magnesium hydroxide, %, minimum	99,8*
3 Mass fraction of volatile substance at 105°C, %, maximum	0,3
4 Mass fraction of iron (Fe), ppm, maximum	50
5 Mass fraction of calcium (Ca), ppm, maximum	100
6 Mass fraction of chlorides (Cl^-), ppm, maximum	200
7 Mass fraction of sulfur (S), ppm, maximum	200
8 Mass fraction of sodium (Na), ppm, maximum	200
9 Bulk density, g/cm^3, minimum	0,3
10 Specific surface area, m^2/g	6,0 - 9,0
11 Filter screening test (no 0045), %, maximum	0,1
12 Particle size distribution, μm:	
diameter of 10 % of particles (d10) maximum	1,1
diameter of 50 % of particles (d50) maximum	2,0
diameter of 90 % of particles (d90) maximum	4,0
13 Surface treatment	Silane Coated

*The norm is given as uncoated product

The material is produced as a tailor-made system. There is a strong producer/customer cooperation

CERTIFICATION:

ISO 9001; ISO 22000:2005; HACCP Codex Alimentarius; HALAL; KOSHER; REACH 01-2119488756-18-0034

CONTACT DETAILS:

Room T3-2909, No. 166 Minhong Road, Minhang District, Shanghai, ZIP Code: 201102

tel: +86 2150 4908 33 139 2064 3683 (Manager Wang)

e-mail: office@kaustik.cn wanghongchun2008@163.com