MAGNESIUM OXIDE **OxiMag® HA**

APPLICATION:

A vulcanizing agent in rubber production •a filler in production of rubber plastics, putties, adhesives • medicine and perfume • production of chemical agents • cleaning from oil products • production of various magnesium compounds • gas treatment • in food industry as emulsifier, anti-caking additive.

THE BASIC QUALITY PARAMETERS:

Parameter	Grade
	OxiMag® HA
1 Mass fraction of magnesium oxide, %, minimum	99*
2 Mass fraction of calcium oxide (CaO), %, max	0.2
3 Mass fraction of silicon dioxide (SiO_2), %, max	0.05
4 Mass fraction of iron as Fe_2O_3, %, max	0.05
5 Mass fraction of aluminum oxide Al_2O_3, %, max	0.05
6 Mass fraction of chlorine (Cl^-), %, max	0.1
7 Mass fraction of sulfates SO_4 %, max	0.1
8 Mass fraction of sodium + potassium (Na+K), %, max	0.1
9 Loss on ignition (900°C), %, max	7,0
10 Iodine activity, mg iodine/g MgO, not less	150
11 Particle size: sieve residue with screen 325 mesh, %, max	1

*The norm is given based on the calcinated product

The material is produced as a tailor-made system. There is a strong producer/customer cooperation

CERTIFICATION:

ISO 9001; ISO 22000:2005; HACCP Codex Alimentarius; HALAL; KOSHER; REACH 01 -2119488756-18-0034

CONTACT DETAILS:

Room T3-2909, No. 166 Minhong Road, Minhang District, Shanghai, ZIP Code: 201102

tel: +86 2150 4908 33 139 2064 3683 (Manager Wang)

e-mail: office@kaustik.cn wanghongchun2008@163.com